

Jul. 7, 2023

BlueWish Wood Free Paper

Mitsubishi Paper Mills Ltd

Hachinohe Mill

			Estimated Value			Actual Value
標準坪量 GSM		g/m ²	50.0	56.0	60.0	76.2
厚さ Thickness		μm	63.0	71.0	76.0	97.0
密度 Density		g/cm ³	0.79	0.79	0.79	0.79
白色度 Brightness		%	88.0	88.0	88.0	87.8
不透明度 Opacity		%	84.0	86.0	87.0	93.2
玉研平滑度 Oken Smoothness	F	Sec	37	37	37	38
	B		25	25	25	25
ストックサイズ度 Stockigt sizing degree		sec				42.0
色相値 Hue (F) PF-10		L*				91.62
		a*				2.50
		b*				-5.94

Above data is not specification but measured values of the production lot.